



COMMERCIAL TESTING COMPANY

Post Office Box 985 • 1215 South Hamilton Street • Dalton, Georgia 30722
Telephone (706) 278-3935 • Facsimile (706) 278-3936

Standard Method of Test for
Surface Burning Characteristics of Building Materials

ASTM E 84-98

Phantasy Plus

Painted

Report Number 9910288

Test Number 3075-8112

October 15, 1999

Vitrulan Corporation
Waynesboro, Virginia

The ASTM E 84 furnace operated by Commercial Testing Company is recognized by the United States Department of Commerce, National Institute of Standards and Technology (NIST), through the National Voluntary Laboratory Accreditation Program (NVLAP) for compliance with Title 15 of the Code of Federal Regulations, Part 285. These criteria encompass the requirements of ISO/IEC Guide 25 and the relevant requirements of ISO 9002 (ANSI/ASQC Q92-1987).

Commercial Testing Company

Jonathan Jackson
(Authorized Signature)

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced test procedure, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.

TESTED TO BE SURE®
Since 1974

INTRODUCTION

This report is a presentation of results of a surface flammability test on a material submitted by Vitrolan Corporation, Waynesboro, Virginia. The test was conducted in accordance with the American Society for Test and Materials fire test response standard E 84-98, *Surface Burning Characteristics of Building Materials*, sometimes referred to as the Steiner tunnel test. This test is applicable to exposed surfaces such as walls and ceilings. The test is conducted with the specimen in the ceiling position with the surface to be evaluated exposed face down to the ignition source. The method, which is similar to NFPA No. 255 and UL No. 723, is an American National (ANSI) Standard and has been approved for use by agencies of the Department of Defense for listing in the *DoD Index of Specifications and Standards*.

This standard should be used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions and should not be used to describe or appraise the fire-hazard or fire-risk of materials, products, or assemblies under actual fire conditions. However, results of the test may be used as elements of a fire-hazard assessment or a fire-risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard or fire risk of a particular end use.

PURPOSE

The purpose of the test is to determine the comparative surface burning behavior of a material by observing the flame spread along the surface of the specimen. It is intended to provide comparative measurements of surface flame spread and smoke development of materials with that of select grade red oak and inorganic fiber reinforced cement (GRC) board under specific fire exposure conditions. The test exposes a nominal 25-foot long by 18-inch wide test specimen to a controlled air flow and flaming fire adjusted to spread the flame along the entire length of a red oak specimen in 5.50 minutes. During the 10-minute test duration, flamespread over the specimen surface and density of the resulting smoke are measured and recorded. Test results are calculated relative to red oak, which has an arbitrary rating of 100, and GRC board, which has a rating of 0. The test results are expressed as Flame Spread Index and Smoke Developed Index. The Flame Spread Index is defined in ASTM E 176 as "a number or classification indicting a comparative measure derived from observations made during the progress of the boundary of a zone of flame under defined test conditions." The Smoke Developed Index, a term specific to ASTM E 84, is defined as "a number or classification indicating a comparative measure derived from smoke obscuration data collected during the test for surface burning characteristics." There is not necessarily a relationship between the two measurements.

The method does not provide for measurement of heat transmission through the surface tested, the effect of aggravated flame spread behavior of an assembly resulting from the proximity of combustible walls and ceilings, or classifying a material as noncombustible solely by means of a Flame Spread Index.

The zero reference and other parameters critical to furnace operation are verified on the day of the test by conducting a 10-minute test using 1/4-inch GRC board. Periodic tests using NOFMA certified 23/32-inch select grade red oak flooring provide data for the 100 reference.

TEST SAMPLE

The test sample, selected by the client, was identified as **Phantasy Plus**, a textile glass wallcovering with a total weight of 8.2 ounces per square yard. Three test panels, each measuring 2 feet wide by 8 feet in length, were prepared by adhering the material to 5/8-inch USG Firecode Type X gypsum board using a commercially available wallcovering adhesive provided by the client. After drying 24 hours, a coat of white latex paint, provided by the client, was applied using a paint roller with a 1/2-inch nap. A second coat of the latex paint was similarly applied after an additional 24 hours drying time. The

prepared test samples were transferred to storage racks and conditioned to equilibrium in an atmosphere with the temperature maintained at $71 \pm 2^\circ\text{F}$ and the relative humidity at 50 ± 5 percent.

TEST RESULTS

The test results, calculated on the basis of observed flame propagation and the integrated area under the recorded smoke density curve, are presented below. The Flame Spread Index obtained in E 84 is rounded to the nearest number divisible by five. Smoke Developed Indices are rounded to the nearest number divisible by five unless the Index is greater than 200. In that case, the Smoke Developed Index is rounded to the nearest 50 points. Flame spread and smoke development data are presented graphically in the computer print-out at the end of this report.

Test Specimen	Flame Spread Index	Smoke Developed Index
GRC Board	0	0
Red Oak Flooring	100	100
Phantasy Plus	20	0

OBSERVATIONS

Specimen ignition over the burners occurred at 0.72 minute. Surface flame spread was observed to a maximum distance of 4.28 feet beyond the zero point at 1.15 minutes. The maximum temperature recorded during the test was 596°F .

CLASSIFICATION

The Flame Spread Index and Smoke Developed Index values obtained by the ASTM E 84 test are frequently used by code officials and regulatory agencies in the acceptance of interior finish materials for various applications. The most widely accepted classification system is found in the National Fire Protection Association publication NFPA 101 *Life Safety Code*, where:

Class A	0 - 25 Flame Spread Index	0 - 450 Smoke Developed Index
Class B	26 - 75 Flame Spread Index	0 - 450 Smoke Developed Index
Class C	76 - 200 Flame Spread Index	0 - 450 Smoke Developed Index

Class A, B, and C correspond to Type I, II, and III respectively in other codes such as SBCCI, BOCA, and ICBO. They do not preclude a material being otherwise classified by the authority of jurisdiction.

ASTM E 84 TEST DATA

Client: Vitruan Corporation
Test Number: 3075-8112
Material Tested: Phantasy Plus
Date: October 15, 1999

Test Results:

Time to Ignition = 00.72 minutes
Maximum Flamespread Distance = 04.28 feet
Time to Maximum Spread = 01.15 minutes

Flame Spread Index = 20
Smoke Developed Index = 0

